



Technical Data Sheet

Q 20-305 Multi Plus Putty

Characteristics:

Especially creamy fill and fine putty. Adheres to all vehicle surfaces including zinc-coated. Very easy application and shaping, short drying time and excellent sanding properties are main features of this product.

Application:

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2% of BPO hardener. Apply within 3-4 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply over wash primers and one component acrylic products.

Technical data:

Density: 1,81 – 1,83 g/cm³


Color: beige



2004/42/II(b)(250) <250 g/l





Cleaning
60-010



BPO- 2-3%




Pot life
3 -4 min 20°C




20 min 20°C




Hand sanding / dry:
P120 - P280



Machine sanding / dry:
P120 - P280



Shelf life:
12 Month



Store in cool place



Latex / Nitril

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017