



Technical Data Sheet

Q 40-200/210/215 2K-HS High Build Sanding Filler

Charakteristics:

Q 40-200 / 210/215 is a 2K-Express high solid filler with excellent filling properties. Very good adhesion to putties and well sanded, hardened paints.

Super easy to sand.

Suitable for solvent-based and water-based paints.

Application

The substrate must be sanded, clean and free of grease.

Mixing ratio, pressure, nozzle:

Filler Vol. 100: 25 (Q 40-2-HF / HEF): 0-25 (Q 99-200) - pressure 3-4 bar, nozzle 1,6-1,8mm


Technical Data:

Density: 1,60 g/cm³

Dry film thickness: 80-100 my/layer undiluted - 50 my/layer 25% diluted




grey/black/white



100 : 25 : 0-25



HF 20-40 min
HEF 15-35 min




19-50 sek. 20°C
F4 Cup




Clean
60-010/60-011




1,6 - 1,8mm




2-3




<>3-5 min 20°C



HF 1,5-2 h
HEF 1-1,5 h



HF 30 min
HEF 20 min




7 min



dry P400-600



dry P400-600



Store at cool
and dry place



2004/42/IIB(c)(540)<435

Dieses Datenblatt dient nur zu Informationszwecken. Nach unserem Kenntnisstand entsprechen die angegebenen Daten dem neuesten Standard und beruhen auf jahrelanger Erfahrung in der Herstellung unserer Produkte.

Copyright: Q-Company 2019, alle Rechte vorbehalten

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017