



MACROFAN HS SYSTEM

DESCRIPTION

Colour mixing system based on very concentrated BASE COLOURS to mix with BINDERS and obtain a range of high solids polyacrylic solid enamels and coloured filler/sealers offering different characteristics as for drying time, covering power and coverage.

USE

For complete, partial painting and touch-ups of cars, motorcycles, buses and commercial vehicles.

CHARACTERISTICS

- Compact and flexible system allowing you to obtain finished products satisfying any need concerning application, directives, performances and equipment.
- Different products as regards solids content, fast drying and coverage can be obtained.
- The enamels obtained offer excellent light and weather resistance and are easy to apply
- The choice of the most recent pigments allows you to obtain the best colour matching of all circulating fleet of cars
- The obtained colours are free from lead, cadmium, and chrome
- The utilisation of coloured primers/fillers guarantees time and product saving

NOTES

The MACROBASES are high concentration colour bases, whose viscosity can considerably increase if the temperature drops under 15°C or if they are continuously stirred on a mixing machine for a long time. It is always recommended to manually stir brand-new base colours by means of a mixing stick before putting them on the machine.

TOPCOAT MACROFAN	BINDER	RATIO B.COLOUR/ BINDER	HARDENERS		THINNERS / ADDITIVES	
MAC 41	M4001	70/30 Weight	MH100 MH110 MH115 MH120	600 ml	00740 00741 00742 00755	100-150 ml
MAC 1 (out of DIR. 2004/42/CE)	M1000	50/50 Weight	00362 00379 00174	500 g	00740 00741 00742 00755	150-300 g
MAC 5	M5000	30/70 Weight	/	/	00551 00740 00741	800-1000 g
MAC 14	M1004	40/60 Weight	00379 00362 00174	250 g	00740 00741 00742 00755	200-250 g
			MH400 MH410 MH415	150 g		250-300 g
			MH100 MH110 MH115 MH120	200 g		200-250 g
MAC 15	M1005	50/50 Weight	00379 00362 00174	250 g	00740 00741 00742 00755	150-200 g
			MH400 MH410 MH415	150 g		200-250 g
			MH100 MH110 MH115 MH120	200 g		150-200 g
MAC 16	M1006	50/50 Weight	00379 00362 00174	250 g	00740 00741 00742 00755	150-200 g
			MH400 MH410 MH415	150 g		200-250 g
			MH100 MH110 MH115 MH120	200 g		150-200 g

SYSTEM

PRIMER FILLER MACROFAN	BINDER	RATIO BASE COLOUR/ BINDER	HARDENERS		THINNERS / ADDITIVES	
MAC 6	M6000	10/90 Vol.	MH100 MH110 MH115 MH120	130 g	00740 00741 00742	100-200 g
			MH600	330 g	MT600	270 g
MAC 71	M7010	10/90 Vol.	00379 00362 00174 MH100 MH110 MH115 MH120	160 g	00740 00741 00742 00755	100-200 g
			MH400 MH415	130 g		
MAC 81	M8011	10/90 Vol.	MH100 MH110 MH115 MH120	110 g	00740 00741 00742	250-300 g W/W 100-200 g D/D
			MH300	180 g	MT300	500 g W/W-D/D
MAC 9	M9000	10/90 Vol.	MH400 MH410 MH415	250 g	00740 00741 00742 00755	250-300 g
			MH100 MH110 MH115 MH120	300 g		200-250 g
MAC 0	M0000	10/90 Vol.	/	/	00526	1000-1300 g

TECHNICAL DATA SHEET N° 0441-GB
UPDATED 03/2019

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.

ISOFAN HS SYSTEM



DESCRIPTION

Polyvalent system for industrial vehicles utilising HS Primers, Fillers and Topcoats.
The system is composed of 31 MACROBASE base colours of high pigment concentration and 6 BINDERS satisfying the market needs requiring low V.O.C emission products.
From this system chrome and lead free products can be obtained.

CONVERTERS

TK 100 ISOFAN HS PRIMER 2K epoxy-acrylic anticorrosive primer for D/D and W/W systems
TK 200 ISOFAN HS SEALER 2K acrylic sealer for high solids W/W and D/D systems
TK 300 ISOFAN HS FILLER High solids 2K sealer/filler for D/D systems
TK 400 ISOFAN ULTRA HS TOPCOAT Very high solids 2K solid topcoat
TK 500 ISOFAN HS TOPCOAT 2K acrylic topcoat of high aesthetical aspect
TK 550 ISOFAN HS MATT 2K acrylic matt topcoat

COLOUR RANGE

About 3000 solid colours used in the sector of Industrial Vehicles are available: RAL 841 GL, Industrial Vehicles, PIAGGIO Commercial Vehicles, AGRICULTURAL MACHINES.

NEW MASTER CHROMA: colour tool dedicated only to this system containing a colour range of about 3000 solid colours, selected among the most used colours in the industrial field and set in chromatic order sprayed on chips and gathered into a practical case (about 25 colour fans). NEW MASTER CHROMA colour range is not updatable.

The MACROBASES series has been strictly tested and is able to guarantee constant colour matching. The cans, complete with a stirring lid and a measuring device, can be put on a stirring machine.

The BINDERS are available in 2.5 lt cans complete with stirring lid and measuring device and can be put on a machine for mechanical stirring.

WARNING

We recommend to wait at least 15 days before submitting to severe conditions (water, humidity or chemical substances) the manufactures which have been painted with 2K products and dried at temperatures according to the relevant technical data sheets.

NOTES

The MACROBASES are high concentration colour bases, whose viscosity can considerably increase if the temperature drops under 15°C or if they are continuously stirred on a mixing machine for a long time. It is always recommended to manually stir brand-new base colours by means of a mixing stick before putting them on the machine.

To manage and obtain a colour it is recommended to choose the colour after checking its colour reference on our colour tools; then, after obtaining the product according to the Lechler MAP or Explorer formulation, apply the product catalysed and thinned as per TDS until complete coverage has been achieved and compare it when thoroughly dried with the colour reference under optimal light conditions. If necessary, proceed with colour correction. Avoid painting manufactured items without any previous colour check.

PRODUCT CODE	BINDER CODE	NAME	CHARACTERISTICS	RATIO BY VOLUME BINDER / B.C.	CATALYSIS BY WEIGHT	CATALYSIS BY VOLUME	HARDENER CODE	THINNER TYPE AND % BY VOLUME
IS01	TK 100	ISOFAN HS PRIMER	2K Anticorrosive primer	90 / 10	13%	20%	TH 810/815	00824 30-35
IS02	TK 200	ISOFAN HS SEALER	2K Sealer	90 / 10	15%	25%	TH 810/815	00824 40-45
IS03	TK 300	ISOFAN HS FILLER	2K Filler/Sealer	90 / 10	13%	20%	TH 810/815	00824/ 5 30-35
				RATIO BY WEIGHT BINDER / B.C.				THINNER % BY WEIGHT
IS04	TK 400	ISOFAN ULTRA HS TOPCOAT	Very high solids 2K solid topcoat	35 / 65	50%	50%	TH 810/815	00824/ 5 15-25
IS05	TK 500	ISOFAN HS TOPCOAT	2K Acrylic topcoat with high aesthetical aspect	50 / 50	50%	50%	TH 710/715	00824/ 5 20-25
IS055	TK 550	ISOFAN HS MATT	2K Acrylic matt topcoat	60 / 40	20%	20%	TH 810/815	00824/ 5 50-60

TECHNICAL DATA SHEET N° 0626-GB
UPDATED 07/2016

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.