CLEARCOATS

96231 TIXOCLEAR PEARL







Ø 1.2-1.4 -mm 3.5-4 Atm N° coats: 2



Low bake at 80°C: 40'

Pot life at 20°C: 4 h

DESCRIPTION

2K glossy pearl clearcoat for two-coat or three-coat systems.

USE

Painting of manufactured items and objects of the habitat field, sporting equipment, lighting hardware, helmets and motorcycles. It features high gloss and an original as well as an exclusive pearl effect to the painted manufactured item.

Apply only on matt basecoats.

CHARACTERISTICS

- · Easy application with no clouding
- Excellent light and weather resistance
- Excellent gloss and good vertical stability
- Full-bodied film

APPLICATION

By spray.

Mixing ratio:

96231 TIXOCLEAR PEARL 00498 INDURITORE AD/MN or 29355 LECHSYS ACRITOP STANDARD HARDENER 00825 LECHSYS UNIVERSAL STANDARD THINNER

Pot life at 20°C: 4 hours

Spray viscosity: 19" FORD Cup 4

Ø Air cap: 1.2 -1.4 mm Air pressure: 3.5- 4 Atm

N° of coats: 2

Interval between coats: 5 –10 min. Recommended film thickness: 35-45 μ Application condition: 20-25°C 50-70% R.H. Theoretical coverage: 1 l mixture 8 m² at 45 μ V.O.C. of the mixture ready for use = 565 g/l

Weight / Volume

1000 parts 500 parts

100 parts

DRYING TIME

Flash-off: 15 min. at 20°C Low baking: 40 min. at 80°C

TECHNICAL DATA

SOLIDS CONTENT ASTM D 1644: 47% parts by weight HARDNESS ASTM D 1522: 96 Oscillations GLOSS 60° ASTM D 523: 96 Gloss

TECHNICAL DATA SHEET N° 0682-GB UPDATED 10/2018

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.